

**CORDAGE POLYPROPYLENE**

REF. **COPP**



Désignation	Diamètre mm	Rupture kg	pois kg/ml
06*	6	600	0.017
08*	8	1 050	0.030
10	10	1 560	0.045
12	12	2 220	0.065
14	14	3 060	0.090
16	16	3 840	0.115
18	18	4 890	0.148
20	20	5 580	0.180
22	22	6 750	0.220
24	24	7 890	0.260
28	28	10 500	0.355
32	32	13 300	0.460

\* Cordage 3 torons pour les diamètres 06 et 08. Au-delà, cordage 4 torons.

**CORDAGE POLYAMIDE**

REF. **CONY**



Désignation	Diamètre mm	Rupture kg	pois kg/ml
06	6	750	0.023
08	8	1 350	0.042
10	10	2 080	0.065
12	12	3 000	0.094
14	14	4 100	0.128
16	16	5 300	0.166
18	18	6 700	0.210
20	20	8 300	0.260
22	22	10 000	0.315
24	24	12 000	0.375
26	26	13 974	0.440
28	28	15 800	0.510
32	32	20 000	0.665

**DRISSE POLYAMIDE**

REF. **CODN**



Désignation	Diamètre mm	Rupture kg	pois kg/ml
02	2	88	0.002
2.5	2.5	115	0.003
03	3	180	0.005
04	4	304	0.008
05	5	530	0.014
06	6	765	0.022
08	8	1 100	0.039
10	10	1 500	0.056
12	12	2 100	0.082

**ATTENTION : Textes et photos non contractuels, susceptibles de modifications sans préavis. Valeurs données à titre indicatif.**